

LOCTITE STYCAST U 2500 HTR

March 2021

PRODUCT DESCRIPTION

LOCTITE STYCAST U 2500 HTR provides the following product characteristics:

Technology	Polyurethane
Appearance, Resin (Component A)	Black
Appearance, Hardener (Component B)	Amber
Components	Two-component
Mixing Ratio, by weight Component A: Component B	100 : 7.6
Product Benefits	<ul style="list-style-type: none"> • Low viscosity • Low modulus • High temperature resistance • Excellent wetting properties
Cure	Room Temperature or Heat Cure
Application	Potting, Encapsulation
Operating Temperature	-40 to +150
Typical Assembly Applications	Transformers, PCB's and other insulating applications

LOCTITE STYCAST U 2500 HTR flexible polyurethane encapsulant is formulated to have low viscosity and excellent wetting properties allowing complete impregnation of either small slightly wound coils or large castings. It can also be used to replace silicones. LOCTITE STYCAST U 2500 HTR has a higher service temperature than standard polyurethane materials.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties

Viscosity @ 25 °C, mPa·s (cP)	12,500
Density, g/cm ³	1.42
Flash Point - See SDS	

Part B Properties

Viscosity @ 25 °C, mPa·s (cP)	135
Density, g/cm ³	1.23
Flash Point - See SDS	

Mixed Properties

Mixed Viscosity @ 25°C, mPa·s (cP)	8,000
Pot Life @ 25°C, hours	4
Shelf Life @ 18 to 25°C, days	183
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE AS MIXED

Recommended Cure Schedule

24 hours @ 25°C or
4 hours @ 60°C

Post Cure

2 hours @ 100 to 120°C

Complete cure at room temperature will be obtained after 2 to 3 days.

A post cure of 2 hours @ 100 to 120°C is recommended.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL AS MIXED

Physical Properties

Hardness, Shore A @ 25°C	75
Coefficient of Thermal Expansion, ppm/°C:	
Above Tg	134
Glass Transition Temperature, °C	-50
Thermal Conductivity, W/(m·K)	0.5
Moisture Absorption, %:	
@ 24°C, 24 hours	0.6
@ 100°C, 1 hour	0.6
Elongation, %	66
Young's modulus (E)	N/mm ² 10 (psi) (1,450)

Electrical Properties

Volume Resistivity@ 500 Volts, ohms-cm	1.7×10 ¹²
Surface Resistivity, ohms	1.9×10 ¹³
Dielectric Constant / Dissipation Factor @ 25°C:	
50 Hz	7.0 / 0.05
1kHz	7.1 / 0.03
1 MHz	6.0 / 0.05

TYPICAL PERFORMANCE OF CURED MATERIAL AS MIXED

Shear Strength

Lap Shear Strength, Al to Al	N/mm ² 6 (psi) (870)
------------------------------	------------------------------------

Miscellaneous

Tensile Strength	N/mm ² 4 (psi) (580)
------------------	------------------------------------

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Directions for Use

1. Moisture sensitive before mixing.
2. Before use, stir Part A to make it homogeneous.
3. Accurately weigh out the required amount of part A and part B as stated in the mix ratio.
4. Mix thoroughly, degas and fill the casting.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 18 to 25 °C

Once opened, containers should be purged with dry nitrogen.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb/F}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.1